



BioClean™ Legion Non-sterile Latex Gloves - BLA3

CHEMICAL PERMEATION REPORT

Permeation breakthrough times according to EN ISO 374:2016

CHEMICAL AGENT	CAS NUMBER	MEAN BREAKTHROUGH TIME (MINUTES)	PROTECTIVE INDEX	PART
Sodium Hydroxide NaOH 40%	1310-73-2	>480	6	Palm
Formaldehyde 37%	50-00-0	>480	6	Palm
Ethanol 70%		19	1	Palm
Isopropyl alcohol (IPA) 70%	67-63-0	5	0	Palm
Ammonia 25%	1336-21-6	<5	0	Palm
Methanol 99.8%		3	0	Palm

Historical permeation data according to EN 374-3:2003

CHEMICAL AGENT	CAS NUMBER	MEAN BREAKTHROUGH TIME (MINUTES)	PROTECTIVE INDEX	PART
Isopropyl alcohol (IPA) 70%	67-63-0	9	1	Palm

RATING SYSTEM						
0	1	2	3	4	5	6
<10	10-30	30-60	60-120	120-240	240-480	>480
NOT RECOMMENDED	SPLASH PROTECTION		MEDIUM PROTECTION		HIGH PROTECTION	

Data given in the table above are based on results of laboratory tests performed on the palm or cuff area of the glove. These tests were run using standard test methods that may not adequately replicate any specific conditions of end use. We wish to highlight that permeation times do not equate to safe wear time. Safe wear time may vary depending on whether the PPE is donned correctly, the surrounding temperature, the chemicals' toxicity, and other factors. Permeation information offered here is limited to the main protective material. Permeation times may vary around seams, zips, visors or any other joins or components of the PPE. It is the responsibility of your organization's Health and Safety professional to undertake a risk assessment before choosing the appropriate PPE for the task at hand. Because Ansell has no detailed knowledge or control over the conditions of end use, any of these data must be advisory only, and Ansell must decline any liability.

Contact your Ansell representative for ordering or more information.

Email: luvas.medicas@ansell.com

North America US Tel: 800 952 9916 CA Tel: 1-844-494-7854 Email: insidesalesus@ansell.com Central & South America Tel: +52(442) 296 20 50 Email: cslac@ansell.com Brazil Tel: +55-11-3356-3100

Europe, Middle East & Africa Tel: +32 (0) 2 528 74 00 Email: info@ansell.eu

Asia Pacific Tel: +603 8310 6688

Australia & New Zealand Tel: +61 3 9270 7270